



RUKN AL ABDA PAPER TRADING L.L.C

ركن الابداع لتجارة الورق ذ.م.م

+971 4 60564444 **info@rapg-uae.com**

Testliner Paper

Technical Specifications											
PROPERTIES	UNIT	TARGET VALUES									
Grammage	g/m2	90	100	112	120	125	135	140	150	175	200
Moisture	%	8	8	8	8	8	8	8	8	8	8
Bursting Strength	kPa	205	225	255	275	285	305	325	330	370	390
RCT CD	N	100	135	160	170	180	190	200	240	270	300
SCT CD	kN/m	1.53	1.70	1.90	2.04	2.13	2.30	2.38	2.48	2.78	3.00
Cobb (60 sec)	g/m2	35	35	35	35	35	35	35	35	35	35

PROPERTIES	UNIT	TEST STANDARD	TOLERANCES
Grammage	g/m2	ISO: 536	±2%
Moisture	%	ISO: 287	±1%
Bursting Strength	kPa	ISO: 2758	±20%
RCT CD	N	ISO: 12192	±12%
SCT CD	kN/m	ISO: 9895	±0.4%
Cobb (60 sec)	g/m2	ISO: 535	±9%

Standard Test Conditions (ISO 187): Temp 23±1 °C and Relative humidity 50±2%